



PLY FORM IRELAND

Your Leading Plyform Suppliers

MILL TEST RESULT

SAMPLE DAY: 16TH March 2017

PRODUCT: EUCALYPTUS HARDWOOD FILM FACED PLYWOOD 18MM (MUF)

NO.	TEST AREA	UNIT	METHOD	RESULT
1	HUMIDITY	%	EN322	10
2	DENSITY	KG/M3	EN323	640
3	SWELLING IN THICKNESS AFTER 24 HOURS IMMERSION IN WATER	%	EN317	4,10
4	BENDING STRENGTH	MPa	EN310	58,0
5	PERPENDICULAR BENDING FORCE	MPa	EN319	0,61
6	FORCE HOLDING SCREWS	N	EN320	2946
7	BONDING QUALITY	MPa	EN314-2	1,90