



**PLY FORM IRELAND**

Your Leading Plyform Suppliers

## **MILL TEST RESULT**

SAMPLE DAY: 16<sup>TH</sup> March 2017

PRODUCT: FILM FACED PLYWOOD 18MM (MUF)

<b>NO.</b>	<b>TEST AREA</b>	<b>UNIT</b>	<b>METHOD</b>	<b>RESULT</b>
1	HUMIDITY	%	EN322	10
2	DENSITY	KG/M3	EN323	640
3	SWELLING IN THICKNESS AFTER 24 HOURS IMMERSION IN WATER	%	EN317	4,10
4	BENDING STRENGTH	MPa	EN310	58,0
5	PERPENDICULAR BENDING FORCE	MPa	EN319	0,61
6	FORCE HOLDING SCREWS	N	EN320	2946
7	BONDING QUALITY	MPa	EN314-2	1,90